



# Registration Certificate

Carpet Name: **DAWSON FALLS**

Licensee: **EC CARPETS**

Licence Number: **1308**

Label Number: **24401**

ACCS Contract Grading: **CLD 1\***

ACCS Residential Grading: **RHD2 4\***

Suitable for Stairs: **Yes**

Date Printed: **30/10/2024**



**Andrew Martin**  
Secretary ACCS



Administered by the Carpet Institute of Australia Limited ABN 11 006 829 303

PO Box 7172, St Kilda Road, Melbourne Victoria 3004 Tel: (03) 9804 5559

Email: [info@carpetoz.com.au](mailto:info@carpetoz.com.au) • [www.carpetinstitute.com.au](http://www.carpetinstitute.com.au)

This certificate remains the property of the Carpet Institute of Australia Limited.

Names:

DAWSON FALLS

Details:

Awarded Res Grade: RHD2 4\*  
Awarded Con Grade: CLD 1\*  
Registered On: 24/10/2024  
Active: Yes  
Date In-Active:  
Manufacture Method: Tufted  
Twist Set: N/A  
Dyeing Method: Loose Fibre  
#Colours/Designs: 9  
Backing Type: Sec Fabric  
Felted: N/A  
Spinning System: Woollen  
Insect Resist Agent: Other  
Filament: 32-36  
Master Product:

Test Results:

Pile Mass g/m² (oz/yd²): 1360 (40.1)  
SPM g/m² (oz/yd²): 935 (27.6)  
Stated Pile Height (mm): 10.0  
Minimum Pile Height (mm): 3.0  
Maximum Pile Height (mm): 10.0  
Dynamic Loading Loss (%): 0.0  
Static Loading Loss (%): 0.0  
Tex (g/1000m): 1300  
Measured Pile Thickness (mm): 7.0  
Machine Gauge (Tufts/dm): 15.7  
Meas Tufts Perp to Selvedge: 21.3  
Meas Tufts Para to Selvedge: 32.2  
Treated For Soiling Resistance: No  
Soil Resist Inhibitor: No  
Stain Resist Inhibitor: No

Hexapod Scores:

Texture		Colour		Thickness	
WA		WA		(mm)	(%)
1500:	3.5 3.5	4.0 4.0	1.3	18.9	
8000:	2.0 2.0	2.5 2.5	2.8	40.3	

Quality Assurance Test:

Cut Pile (%): 0  
Loop Pile (%): 100  
Panel Assessment Contract: 12  
Panel Assessment Residential: 12  
Suitable For Stairs: Yes  
Tile: No SheetGoods: No  
Fibre Signature: WOO:100

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	9.4	12.7	16
Volume Density:	17.5	17.5	20
Tuft Density:	2.5	2.5	9
Dyn Load:	3.9	3.9	5
Stat Load:	4.1	4.1	5
Soiling Prop:	14	14	14
Abrasion Res:	5	5	10

Calculations

Pile Height(mm): 7.1  
Tuft Density(per dm²): 685.9  
GSPM(g/m²): 1050.0  
GSPM (abrasive) (g/m²): 1320.0  
Soiling Propensity: 14.0 +0.0

OAF Values

OAF: 2.8  
Calc Density (+-5%):0.13 0.134 0.14  
Base Fibre: WOOL  
Benchmarks:  
RHD1 0 RHD2 2.7  
REHD1 2.7 REHD2 3

Environmental Classification:

ECS:  
Level:  

	Calc	B/M	P/F
Acoustic:	7	4	PASS
Thermal:	52.4	20	PASS
VOC:			
TVOC	0		

Notes:

24/10/2024 Submitted by A Turner. 30/11/2024 Panel awarded CLD(S) 1\* and RHD2(S) 4\*.