



# Registration Certificate

Carpet Name: **HAUSE**

Licensee: **EC CARPETS**

Licence Number: **1308**

Label Number: **21207**

ACCS Contract Grading: **CMD 2\***

ACCS Residential Grading: **REHD1 5\***

Suitable for Stairs: **Yes**

Date Printed: **26/05/2021**



*Allan Firth*



**Allan Firth**  
Secretary ACCS



**Administered by the Carpet Institute of Australia Limited** ABN 11 006 829 303

PO Box 7172, St Kilda Road, Melbourne Victoria 8004 Tel: (03) 9804 5559 • Fax: (03) 9804 5560

Email: [info@carpetoz.com.au](mailto:info@carpetoz.com.au) • [www.carpetinstitute.com.au](http://www.carpetinstitute.com.au)

This certificate remains the property of the Carpet Institute of Australia Limited.

Names:  
HAUSE

Details:

Awarded Res Grade: REHD1 5\*  
Awarded Con Grade: CMD 2\*  
Registered On: 24/05/2021  
Active: Yes  
Date In-Active:  
Manufacture Method: Tufted  
Twist Set: N/A  
Dyeing Method: Loose Fibre  
#Colours/Designs: 8  
Backing Type: Sec Fabric  
Felted: N/A  
Spinning System: Woollen  
Insect Resist Agent: Permethrin  
Filament: 32-36  
Master Product:

Hexapod Scores:

Texture		Colour		Thickness	
WA		WA		(mm)	(%)
1500:	3.5 3.5	4.0 3.5	1.0	18.2	
8000:	2.0 2.0	3.0 3.0	2.2	39.5	

ACCS Test:

	Con	Res	Max
SPM/PH Ratio:	9.5	12.8	16
Volume Density:	16.9	16.9	20
Tuft Density:	2.3	2.3	9
Dyn Load:	3.9	3.9	5
Stat Load:	4.1	4.1	5
Soiling Prop:	14	14	16
Abrasion Res:	4.4	4.4	10
Sub Total:	55.1	58.4	81
Panel Assess:	12	12	19
Total:	67.1	70.4	100
Calc Residential Grade:	REHD1	5*	
Calc Contract Grade:	CLD	1*	

Test Results:

Pile Mass g/m² (oz/yd²): 1360 (40.1)  
SPM g/m² (oz/yd²): 824 (24.3)  
Stated Pile Height (mm): 8.0  
Minimum Pile Height (mm): 0.0  
Maximum Pile Height (mm): 0.0  
Dynamic Loading Loss (%): 0.0  
Static Loading Loss (%): 0.0  
Tex (g/1000m): 1400  
Measured Pile Thickness (mm): 5.6  
Machine Gauge (Tufts/dm): 21.0  
Meas Tufts Perp to Selvedge: 21.2  
Meas Tufts Para to Selvedge: 21.6  
Treated For Soiling Resistance: No  
Soil Resist Inhibitor: No  
Stain Resist Inhibitor: No

Quality Assurance Test:

Cut Pile (%): 0  
Loop Pile (%): 100  
Panel Assessment Contract: 12  
Panel Assessment Residential: 12  
Suitable For Stairs: Yes  
Tile: No SheetGoods: No  
Fibre Signature: WOO:100

Calculations

Pile Height(mm): 6.5  
Tuft Density(per dm²): 457.9  
GSPM(g/m²): 960.0  
GSPM (abrasive) (g/m²): 1320.0  
Soiling Propensity: 14.0 +0.0

OAF Values

OAF: 2.8  
Calc Density (+-5%):0.14 0.147 0.15  
Base Fibre: WOOL  
Benchmarks:  
RHD1 0 RHD2 2.7  
REHD1 2.7 REHD2 3

Environmental Classification:

ECS:  
Level: 0

	Calc	B/M	P/F
Acoustic:	5.6	4	PASS
Thermal:	38.1	20	PASS
VOC:			
TVOC	0		

Notes:

24/5/21 Submitted by K Grace. 26/5/21 Panel graded CMD(S) 2\*and REHD1(S) 5\*.