

ATTAR

Advanced Technology Testing and Research

ATTAR TEST REPORT NUMBER: 14/8088.12



The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards. Accredited for compliance with ISO/IEC 17025. Accreditation Number: 2735

24 July 2014

WET PENDULUM SLIP RESISTANCE

Job No: M14/8088

Total Pages: 2

Prepared for:	Regupol Australia Pty Ltd					
•	155 Smeaton Grange Road					
	SMEATON GRANGE NSW 2567					
Attention:	Kelly Mahon					
Test Site:	Test Slip Australia Pty Ltd, Beaumont Hills, NSW.					
Test Date:	22 July 2014					
Test Specimens, Size &	everroll® Shape I Uni – 4mm thickness, unsealed,					
Quantity:	300mm x 300mm, 5 off supplied.					
Sampling & Direction of Testing:	Sampling conducted by client. Test direction not					
	applicable. Refer to Figure 1.					
Test Personnel:	Clark Ahearn					
Preparation:	Washed with water and dried.					
Fixed/Unfixed:	Fixed.					
Air Temperature:	19°C					
Test Equipment:	Wessex Skid Resistance Tester (Pendulum) Serial					
	Number SK 1818, Calibrated 16/8/2012.					
Test Standard:	AS 4586: 2013 Slip resistance classification of new					
	pedestrian surface materials – Appendix A.					
Slider Rubber:	Slider 55 Batch No. #78 prepared on P400 & 3µm					
	lapping film.					
Classification Criteria:	Refer to Classification Criteria, attached as Appendix 1.					
	Specimen Number					CDV
British Pendulum Number	1	2	3	4	5	SRV
	37	35	41	42	46	40
Classification:	P4					

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

NOTE: Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

ATTAR

Marcus Braché Senior Engineering Technician Approved Signatory



ATTAR TEST REPORT NUMBER: 14/8088.12

24 July 2014

Total Pages: 2



Figure 1: everroll® Shape | Uni – Highlighted area indicates area tested and direction of test.