AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client : Beaulieu of 166 Pearsor Yatala QLD			lssue Print		23-00044 2/02/2023 2/02/2023 36077	3	
Sample Description	Clients Ref : "Serenity Shores - N Cut pile carpet Nominal Composition : 100% Re Nominal Mass per Unit Area/Density	sistain Solution					
ISO 9239.1:2010 Part 1	Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source						
	Date of Sample Arrival		15-10-	-2019			
	Date Tested		20-04-2020				
	CHF Value	1	2	3	Mean		
	Length	6.4	5.0	4.6	5.3	kW/m²	
	Width	6.9	-	-	-	kW/m²	
	HF-30 Value	1	2	3	Mean		
	Length	-	-	4.6	-	kW/m²	
	Width	-	-	-	-	kW/m²	
	Smoke Value	1	2	3	Mean		
	Length	178	198	192	189	%.min	
	Width	154	-	-	-	%.min	
	Observations						
	Melting				Yes		
	Penetration of flame through to subs	trate			Yes		

288111

62807

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Deld

Fiona McDonald



Page 1 of 2

MICHAEL A. JACKSON B.Sc.(Hons)



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

## **TEST REPORT**

Client :	Beaulieu of Australia Limited	Test Number :	23-000440
	166 Pearson Road	Issue Date :	2/02/2023
	Yatala QLD 4207	Print Date :	2/02/2023
		Order Number :	36077

Each specimen was loose laid over Dunlop - Government Red underlay and 6mm thick fibre reinforced cement board and clamped prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 9.4 have not been included in the report. They are available upon request.

288111

62807

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

12

Fiona McDonald





Page 2 of 2

IICHAEL A. JACKSON B.Sc.(Hons)