

SLIP RESISTANCE TEST REPORT

Client: Jacobsens Creative Surfaces
Client's Reference: Natalie SO160485

Tested By: Kevin Stackhouse
Date: **26 June 2014**

DESCRIPTION OF SAMPLE

Manufacturer: Marazzi
Common Name: Sistem N20
Specimen Size: 600 x 600mm
No. of Specimens Tested. 4

Material Type: Porcelain
Surface Type: Grip
Colour: Grigio Scuro
Surface Coating: Nil

METHOD

Tests were carried out in accordance with AS/NZS 3661.1 : 1993 Slip Resistance of Pedestrian Surfaces, Part 1- Requirements, Appendix A "Method for the Measurement of the Coefficient of friction of Wet Surfaces".

Type of Test: **Wet**

Location of Test: 19b Neil Park Drive

Air Temperature: °C18

East Tamaki

RESULTS

Specimen No.	Dilution Ratio	Dwell Time	Mean Coefficient of Friction
one			0.60
two			0.60
three			0.57
four			0.60
five			0.00

SAMPLE MEAN COEFFICIENT OF FRICTION: 0.59

REQUIREMENTS

Horizontal Surfaces: When tested in accordance with the method set out in Appendix A, the pedestrian surface shall have a mean coefficient of friction of not less than **0.40** and no specimen in that sample shall be less than **0.35**.

COMMENTS:

SAFETY STEP (NZ) LTD

THE ULTIMATE IN ANTI-SLIP AND WAY FINDING SYSTEMS