

## Reaction to fire classification report

### 1 Introduction

This classification report defines the classification assigned to the product Primo SD in accordance with the procedure given in EN 13501-1:2018.

### 2 Details of classified product

#### 2.1 General

The product Primo SD is defined as a floor covering. Its classification is valid for the following end use application: Floor covering.

#### 2.2 Product description

The product, Primo SD, is fully described in the test report provided in support of classification listed in Clause 3.1.

### 3 Test report

#### 3.1 Test report

This classification is based on the test report listed below:

Name of laboratory	Name of sponsor	Test report ref no	Accredited test method
RISE	Tarkett AB	9P04130-4	EN ISO 9239-1:2010 EN ISO 11925-2:2010/AC:2011

## RISE Research Institutes of Sweden AB

Postal address  
Box 857  
SE-501 15 BORÅS  
SwedenOffice location  
Brinellgatan 4  
SE-504 62 BORÅSPhone / Fax / E-mail  
+46 10 516 50 00  
+46 33 13 55 02  
info@ri.se

This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

**3.2 Test results**

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean (m)	Compliance parameter
EN ISO 11925-2 15 s exposure	$F_s \leq 150$ mm	6	(-)	Compliant
EN ISO 9239-1	<i>Critical flux</i> (kW/m <sup>2</sup> )	4	11	Compliant
	<i>Smoke</i> (%.min)		127	Compliant

(-) : not applicable

**4 Classification and field of application**

**4.1 Reference and direct field of application**

This classification has been carried out in accordance with clause 12 and 15 of EN 13501-1:2018.

**4.2 Classification**

The product called “Primo SD” in relation to its reaction to fire behaviour is classified:

$B_{fl}$

The additional classification in relation to smoke production is:

s1

The format of the reaction to fire classification for floorings is:

Fire Behaviour		Smoke Production	
		s	1
$B_{fl}$	-	s	1

**Reaction to fire classification:  $B_{fl-s1}$**

#### 4.3 Field of application:

This classification is valid for the following product parameters:

Nominal thickness: 2.0 mm.

Nominal area weight: 3000 g/m<sup>2</sup>.

This classification is valid for the following end use applications:

Substrates

- Wood based substrates at least 18 mm thick or substrates of Euroclass A1<sub>fl</sub> or A2<sub>fl</sub> at least 6 mm thick, having a density  $\geq 510$  kg/m<sup>3</sup>.

The sample was delivered by the client. RISE Safety – Fire Research was not involved in the sampling procedure.

#### 5 Limitations

This classification document does not represent type approval or certification of the product.

### **RISE Research Institutes of Sweden AB Safety - Fire Research Materials**

Performed by

Examined by

Kristian Törnqvist

Per Thureson