

Reaction to fire classification report

1 Introduction

This classification report defines the classification assigned to the product Primo Safe.T in accordance with the procedure given in EN 13501-1:2018.

2 Details of classified product

2.1 General

The product Primo Safe.T is defined as a floor covering. Its classification is valid for the following end use application: Floor covering.

2.2 Product description

The product, Primo Safe.T, is fully described in the test report provided in support of classification listed in Clause 3.1.

3 Test report

3.1 Test report

This classification is based on the test report listed below:

Name of laboratory	Name of sponsor	Test report ref no	Accredited test method
RISE	Tarkett AB	9P04130-2	EN ISO 9239-1:2010 EN ISO 11925-2:2010/AC:2011

RISE Research Institutes of Sweden AB

Postal address	Office location	Phone / Fax / E-mail
Box 857	Brinellgatan 4	+46 10 516 50 00
SE-501 15 BORÅS	SE-504 62 BORÅS	+46 33 13 55 02
Sweden		info@ri.se

This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

3.2 Test results

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean (m)	Compliance parameter
EN ISO 11925-2 15 s exposure	$F_s \leq 150$ mm	6	(-)	Compliant
EN ISO 9239-1	<i>Critical flux</i> (kW/m ²)	4	11	Compliant
	<i>Smoke</i> (%.min)		152	Compliant

(-) : not applicable

4 Classification and field of application

4.1 Reference and direct field of application

This classification has been carried out in accordance with clause 12 and 15 of EN 13501-1:2018.

4.2 Classification

The product called “Primo Safe.T” in relation to its reaction to fire behaviour is classified:

B_{fl}

The additional classification in relation to smoke production is:

s1

The format of the reaction to fire classification for floorings is:

Fire Behaviour		Smoke Production	
		s	1
B_{fl}	-	s	1

Reaction to fire classification: *B_{fl}-s1*

4.3 Field of application:

This classification is valid for the following product parameters:

Nominal thickness: 2.0 mm.

Nominal area weight: 3000 g/m².

This classification is valid for the following end use applications:

Substrates

- Wood based substrates at least 18 mm thick or substrates of Euroclass A1_{fl} or A2_{fl} at least 6 mm thick, having a density ≥ 510 kg/m³.

The sample was delivered by the client. RISE Safety – Fire Research was not involved in the sampling procedure.

5 Limitations

This classification document does not represent type approval or certification of the product.

RISE Research Institutes of Sweden AB Safety - Fire Research Materials

Performed by

Examined by

Kristian Törnqvist

Per Thureson