
CLASSIFICATION OF REACTION TO FIRE ACCORDANCE WITH EN 13501-1:2018

1. Introduction

This classification report defines the classification assigned to REGUPOL everroll ultimate in accordance with the procedures in EN 13501-1:2018.

Sponsor: REGUPOL Germany GmbH & Co. KG
Am Hilgenacker 24
57319 Bad Berleburg
Germany

Prepared by: SYCHTA LABORATORIUM Sp. J.
Laboratorium Badań Palności Materiałów
ul. Ofiar Stutthofu 90
72-010 Police, Poland

Notified Body No: 3039

Product name: REGUPOL everroll ultimate

Classification report No: SL/Z-445/EN13501/0545a/2026

Date of issue: 22.04.2026

This classification report consists of four pages and may only be used or reproduced in its entirety.

2. Details of classified product

2.1. General

The product, REGUPOL everroll ultimate

2.2. Product description

The product, REGUPOL everroll ultimate, is described below or is described in the reports provided in support of classification listed in 3.1

<p>First set:</p> <p>Grey floor covering (3,7-4,0 mm thick) glued to fiber-cement board (approx. 8,0 mm thick), total thickness of 11,8-12,1 mm and with weight per unit area 19,-19,7 kg/m².</p> <p>Grey floor covering 3,7-4,0 mm thick with weight per unit area approx. 5,2 kg/m².</p> <p>Second set:</p> <p>Grey floor covering (9,5-10,0 mm thick) glued to fiber-cement board (approx. 8,0 mm thick), total thickness of 17,5-18,0 mm and with weight per unit area 27,3-28,2 kg/m².</p> <p>Grey floor covering 9,5-10,0 mm thick with weight per unit area approx.13,2 kg/m².</p>

3. Reports and results in support of this classification

3.1. Specific conditions

-

3.2. Reports

Name of Laboratory	Name of sponsor	Report ref. No.	Test method and date Field of application rules and date
Sychta Laboratorium	REGUPOL Germany GmbH & Co. KG	SL/Z-445/EN9239/0544a/2026	EN ISO 9239-1 EN ISO 11925-2 14-15.04 and 17.04.2026

3.3. Results

Test method and test numer	Parameter	No. Tests ^a	Results	
			Continuous parameter - mean (m)	Compliance with parameters
EN ISO 9239-1	HF-30, kW·m ⁻²	3	8,9	(-)
	Smoke Sc, %·min		16	(-)
EN ISO 11925-2 Exposure time 15 s	Flame spread ≤ 150 mm in 20 s, mm	12	(-)	Compliant

^a Not for extended application, (-): not applicable

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with EN 13501-1:2018.

4.2. Classification

The product, REGUPOL everroll ultimate, in relations to its reaction to fire behaviour is classified:

B_{f1}

The additional classification in relations to smoke production is:

s1

The format of the reaction to fire classification for floorings products is:

Fire behaviour		Smoke production	
B_{f1}	-	s	1

Reaction to fire classification: B_{f1}-s1

4.3. Field of application

This classification is valid for the following product parameters:

REGUPOL everroll ultimate

- EPDM granules bonded with PU binder
- Glued to the fibre cement 8 mm with 2 K PU
- Weight per unit area: 5,5 kg/m² (4 mm); 13,77 kg/m² (10 mm)
- Density: 1377 g/L
- Thickness: 4-10 mm


The classification is valid for the following end use applications:

This classification applies to material glued to the mineral substrates of class A1fl or A2fl-s1/s2 with 2k-Polyurethan Glue.

5. Limitations

This classification document does not represent type approval or certification of the product.

*Signature of person
undertaking classification:*



dr inż. Krzysztof Sychta

*Signature of person
authorising report:*

SYCHTA LABORATORIUM Sp. J.
72-010 Police, ul. Ofiar Stutthofu 90
tel./fax +48 91 4210 214, tel. 502078855
e-mail: biuro@sychta.eu www:sychta.eu
KRS 0000387681 REGON 321023120
NIP 8513152392

KIEROWNIK LABORATORIUM



dr hab. inż. Zygmunt Sychta