AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Tarkett Australia Pty Ltd
Suite 1 Level 3
3 Columbia Court
Baulkam Hills NSW 2153

Test Number : 24-001121
Issue Date : 19/04/2024
Print Date : 19/04/2024

Sample Description

Clients Ref : "Acczent Excellence Compact +"
Vinyl Flooring
End Use : Flooring
Nominal Composition : PVC with foam layer backing
Nominal Mass per Unit Area/Density : 2750g/m2
Nominal Thickness : 2.15mm



319644 69936

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved

Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

0204/11/06

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Tarkett Australia Pty Ltd
Suite 1 Level 3
3 Columbia Court
Baulkam Hills NSW 2153

Test Number : 24-001121
Issue Date : 19/04/2024
Print Date : 19/04/2024

AS ISO 9239.1-2003 **Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source**

Date of Sample Arrival 02-04-2024

Date Tested 19-04-2024

CHF Value	1	2	3	Mean	
Non Directional	6.8	6.8	7.5	7.0	kW/m²

Smoke Value	1	2	3	Mean	
Non Directional	240	244	224	236	%.min

Observation
Blistering Yes

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

No directional properties, three specimens tested only.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved

Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR