

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

Group Number Assessment

(In accordance with New Zealand Building Code Verification Method C/VM2 Appendix A)


This is to confirm that the product as described below has been tested by AWTA Product Testing .

Testing was performed in accordance with ISO 5660.1-2015 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

Test Sponsor : Tarkett Australia Pty Ltd
Suite 1 Level 3
3 Columbia Court
Baulkam Hills NSW 2153

Test Number : 24-002860
Issue Date : 2/08/2024
Print Date : 5/08/2024

Sponsor Product : Rubber tile
Colour : Grey
End Use : Wall tile
Nominal Composition : Rubber
Nominal Mass per Unit Area/Density : Approx: 5.6kg/m2
Nominal Thickness : 3.5mm



72075

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

Group Number Assessment

(In accordance with New Zealand Building Code Verification Method C/VM2 Appendix A)

This is to confirm that the product as described below has been tested by AWTA Product Testing.

Testing was performed in accordance with ISO 5660.1-2015 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

Test Sponsor : Tarkett Australia Pty Ltd
Suite 1 Level 3
3 Columbia Court
Baulkam Hills NSW 2153

Test Number : 24-002860
Issue Date : 2/08/2024
Print Date : 5/08/2024

Product Group Number Classification : 3

Average Specific Extinction Area : 451.2 m²/kg



Chris Campbell
Client Relations Manager

72075

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited. Please contact us by collect call so that arrangements can be made at our expense to rectify the error.