

iQ GRANIT ACOUSTIC

Sample description as provided by customer

Order No. P

Homogeneous vinyl flooring with foam interlayer Wear Layer 2.0mm Total Thickness 3.5 mm Total Weight 3810g/m

TEST METHOD: ISO 9239-1(2010 06-15) Determination of the Burning Behaviour Using a Radiant Heat Source. As required by the New Zealand Building Code Clause C2.1 (January 2017). Sample conditioning as specified in BS EN 13238.2010.

Sample Submitted Date **Jan 2018**

Test Date **08 Feb 2018**

Total Thickness mm

Assembly: DIRECT STICK (Details Below).

The floor covering was directly stuck to the substrate using Vinyl adhesive.

Substrate: Non-Combustible - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring. The Holding Torque on Specimen Frame was 2Nm.

The standard requires two Initial Tests be conducted on samples mounted in both Length and Width directions. Two further samples are then tested in whichever direction has the lowest Critical Radiant Flux.

Initial Tests: **Length** Direction Critical Radiant Flux **10.3 kW/m²**
Width Direction Critical Radiant Flux **9.9 kW/m²**

Specimen Tests conducted in the Width Direction				
	Specimen #1	Specimen #2	Specimen #3	Mean
Critical Radiant Flux (kW/m ²)	9.9	9.9	10.3	10.0

The value quoted below is as required by the New Zealand Building Code Clause C2.1 (January 2017) "Minimum critical radiant flux when tested to ISO 9239-1:2010". Hence the Radiant Flux quoted is the value at Flame-Out/Extinguishment Not after a 30 minute burn as used in Europe.

Mean Critical Radiant Flux **10.0** kW/m²

Observations: The samples shrunk away from the heat source, ignited and burnt a short distance.

ISO 9239-1:2010 Clause 10(o) The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

All information required for compliance with the BCNZ is given on this test report page.

	M. B. Webb Technical Manager	
	DATE: 08 Feb 2018	
	Performance & Approvals Accreditation No. 15393	
	Accredited for compliance with ISO/IEC 17025.	

TIME FOR EACH SPECIMEN TO REACH EACH MARKER IN SECONDS

Specimen	50	60	110	160	210	260	310	360	410	460	510	560	610	660	710	760	810	860
1	133	134	145	166	/													
2	138	139	149	169	/													
3	136	137	164	203	/													

TESTS

BURNING CHARACTERISTICS

Specimen	Burn Length (mm) at Flame Out/ Extinguishment	Time To Burn Out (s)
Initial Test: Length	160	1,316
Specimen Tests: Width		
1	180	1,038
2	180	906
3	160	935
Mean	173	960




M. B. Webb
 Technical Manager

DATE: 08 Feb 2018

Performance and Approvals
 Accreditation No. 15393
 Accredited for compliance
 with ISO/IEC 17025.

2004 04 09 1813 8 February 2018